

GREYKEN LIMESTONE



TEST METHODS	RESULTS
Flexural Strength	Mean Value 23,4 Mpa
Water Absorption	Mean Value 0,4%
Apparent Resistance	Mean Value of Apparent Resistance 2.700 Kg / m³
Compression Resistance	Mean Value of Compression Resistance 160 MPa
Hardness	Mean Value 151,0 Micras
Absorption by Capillarity	Standard Value 0,045 kg / m²xh^{1/2}