


PILA GRANITE



TEST METHODS	RESULTS
Petrographic Examination (UNE-EN 12407)	Granite
Water Absorption (UNE-EN 13755)	0,30%
Apparent Density and Open Porosity (UNE-EN 1936)	2.630 Kgs /m3 - 0,9%
Resistencia a la Abrasión (mm) (UNE-EN 14157)	15,4 MPa
Flexural Strength (UNE-EN 12372)	15,9 MPa
Resistencia a la compresion (UNE-EN 1926)	165 MPa
Frost Resistance (UNE-EN 12371)	after 56 cycles 16,9